

## Guiding Formulation

### Waterdilutable Wood- and Furniture Lacquer

- high rub resistance -

Rec. No.  
33-09050

Date  
12.06.96 /MA

Revised:

-qualified for solid wood-, veneer-, chipboard-, mediumboard- and hardboardcoatings -

1.	Stapa Hydroxal / Hydrolux .....	5,0	www.eckart.net
2.	Tego Wet KL 245	0,3	www.tego.de
3.	Water demin.	4,7	
	pre-disperse		
4.	Jagotex DU 35, 35% in water	53,0	www.eastman.com
5.	Aquacer 526	2,8	www.byk-cera.demon.nl
6.	Tego Glide 440	0,2	www.tego.de
7.	Tego Foamex 805	0,4	"
	homogenize		
8.	Jagotex EM 2245, 46% in water	26,5	www.eastman.com
9.	Water demin.	5,3	
10.	Nuvis FX 1010, 10% in water	1,8	www.elementis-specialties.com
		-----	
		100,0	

Paste pos. 1-3, then homogenize pos. 4-7 and add by stirring slowly.

Add pos. 8-10 to this mixture.

This information is for your advice on conscientiously executed tests. Considering the variety of tests this information is without warranty.

ECKART GmbH & Co. KG  
 Guentersthal  
 D-91235 Velden  
 Fax: ++49 (0) 91 52-77- 45 09  
 Tel.: ++49 (0) 91 52-77- 45-11 oder -0