

Guiding Formulation
2 Pack-system, water dilutable
based on 2 C-Epoxy resin (air drying)

Rec. No.
75-07001

Date
28.11.03 /MI

Revised:

Component I :

Standart Zinflake AT	24,0	www.eckart.net
Dowanol PMA	10,0	www.dow.com
- predisperse -		
Beckopox EP 147w, 100%	10,0	www.surfacespecialties.com
- add while stirring -		

Component II :

Beckopox EH 623w, 80%	10,4	www.surfacespecialties.com
Aerosil R 972	0,5	www.degussa.com
Bentone EW, 3% in demin. water	2,0	www.elementis-specialties.com
Plastorit 0000	8,2	www.luzenac.com
Micro Talkum AT extra	13,4	www.omya.com
demin. water	21,5	
- disperse with dissolver < 20 micro -	-----	
	100,0	

dilute Component II with 10 ml demin. water, incorporate it in Component I and mix both with dissolver.

Spraying viscosity : app. 22 sec, DIN-cup 4 mm
 Diluent : demin. water
 Pot life : app. 60 min

This information is for your advice on conscientiously executed tests. Considering the variety of tests this information is without warranty.

ECKART GmbH & Co. KG
 Guentersthal
 D-91235 Velden
 Fax: ++49 (0) 91 52-77- 45 09
 Tel.: ++49 (0) 91 52-77- 45-11 oder -0