

Guiding Formulation

Water dilutable Reflective Paint**for automotive accessories (reflectors)**Rec. No.
82-09018Date
11.05.99 /MIRevised:
24.10.05 /MI

12.01.06/MI

Component A :

1	WorleeCryl 7135, 42% W - start with pos. 1 -	50,0	www.worlee.de
2	Acrysol RM 8, 30% in H ₂ O demin.	0,6	www.rohmhaas.com
3	Water demin. - blend pos. 2 and 3 and mix into pos. 1 -	13,9	
4	Water demin	10,5	
5	Methoxy propanol - and one after the other while stirring -	5,0	

Component B :

6	Stapa Hydrolac WH Chromal X	10,0	www.eckart.net
7	Water demin. - disperse homogeneously -	10,0 -----	
		100,0	

Add component B to comp. A while stirring.

Sprayviscosity : 22 sec. DIN-cup 4 mm

Diluent : water demin.

Drying : air drying

This information is for your advice on conscientiously executed tests. Considering the variety of tests this information is without warranty.

ECKART GmbH & Co. KG
Guentersthal
D-91235 Velden
Fax: ++49 (0) 91 52-77- 45 09
Tel.: ++49 (0) 91 52-77- 45-11 oder -0