

Guiding Formulation
Metallic basecoat, silver
water based

Rec. No.
76-09007

Date
17.02.00 /CR

Revised:
10.03.05 /KU

a)	Daotan VTW 6462, 36% WA	30,60	www.cytec.com
	DMEA, 10% in water	2,90	
	Water demin.	15,85	
	- stir 10 min. -		
	Viscalex HV 30, 10% *	10,00	
	Water demin.	11,30	
	- stir 10 min. -		
	n-Butanole	1,90	
	Mineral spirit	0,25	
	Water demin.	14,10	
	- stir 10 min. -	-----	
		86,90	
b)	Stapa Hydrolac WH 8154 NL	5,65	www.eckart.net
	Additol XL 250	0,60	www.cytec.com
	Butyl glycol	5,65	
	N-MP	1,20	
	- predisperse -	-----	
		13,10	

Component b) under stirring to a)

This information is for your advice on conscientiously executed tests. Considering the variety of tests this information is without warranty.

ECKART GmbH
 Guentersthal
 D-91235 Velden
 Fax: ++49 (0) 91 52-77- 45 09
 Tel.: ++49 (0) 91 52-77- 45-11 oder -0

Guiding Formulation
Metallic basecoat, silver
water based

Rec. No.
76-09007

Date
17.02.00 /CR

Revised:
10.03.05 /KU

* **Viscalex HV 30, 10% :**

Water demin.	64,5	
DMEA, 10% in water	2,5	
Viscalex HV 30	33,0	www.cibasc.com

	100,0	

Viscosity : with water demin., to 35 sec. DIN cup 4 mm

pH-value : 7,2 – 7,6

This information is for your advice on conscientiously executed tests. Considering the variety of tests this information is without warranty.

ECKART GmbH
Guentersthal
D-91235 Velden
Fax: ++49 (0) 91 52-77- 45 09
Tel.: ++49 (0) 91 52-77- 45-11 oder -0