

Loose Powder - "Subtlement Chocolat"

Color Cosmetics

Ref: CC/0007/EU

Product Name	INCI Name	%W/W	Supplier
A			
		100.00	
Softouch CCS 102	Boron Nitride	38.04	www.advceramicscos.com
Micropoly 250s	Polyethylene	22.15	www.micropowders.com
Kaolin	Kaolin	3.59	www.avokal-heller.de
Covasilic 15	Silica Dimethyl Silylate	0.95	www.lcw.fr
Prestige® Soft Beige	Mica (and) Titanium Dioxide (and) Iron Oxides	25.00	www.eckart.net
B			
Dow Corning 670 Fluid	Cyclopentasiloxane (and) Polypropylsilsesquioxane	5.00	www.dowcorning.com
Dow Corning 1501 Fluid	Cyclopentasiloxane (and) Dimethiconol	2.00	www.dowcorning.com
Aromatic Cocoa Extract G4912WS	Theobroma Cacao (Cocoa) Extract	1.00	www.carrubba.com
ProBioBalance CLR	Water (and) Lactose (and) Milk Protein (and) Bifida Ferment Lysate	2.00	www.clr-berlin.com
Euxyl PE 9010	Phenoxyethanol (and) Ethylhexylglycerine	0.27	www.schuelke-mayr.com

Procedure

1. Mix phase A with speedmixer (30 s/ 2000 rpm)
2. Add phase B to phase A and mix again with speedmixer (30 s/ 2500 rpm)
3. Fill into an appropriate container

Stability

Stable for at least 6 months at RT and 40°C.

Customer Support

ECKART GmbH & Co. KG
info.eckart@altana.com

ECKART Cosmetic Colours LLC
info.eckart.cosmetics@altana.com

ECKART Asia Limited
info.eckart.asia@altana.com

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.