

Pearl Cream Eye Shadow - "Soft Earthy Bronze"

Color Cosmetics

Ref: CC/0009/EU

Product Name	INCI Name	%W/W	Supplier
A			
		100.00	
Castor Oil	Castor Oil	31.70	www.riedeldehaen.com
Liponate EHP	Octyl Palmitate	6.00	www.lipochemicals.com
Lipovol C-76	Cocos Nucifera (Coconut) Oil	7.00	www.lipochemicals.com
Ewacera 12	Bees Wax	6.00	www.wagnerlanolin.de
Ewalan IP	Isopropyl Lanolate	5.00	www.wagnerlanolin.de
Avocado Butter	Persea Gratissima (Avocado) Oil and Hydrogenated Avocado Oil	7.00	www.impag.de
Dow Corning 5562 Carbinol Fluid	Bis-Hydroxyethoxypropyl Dimethicone	7.00	www.dowcorning.com
Dow Corning 9701 Cosmetic Powder	Dimethicone/ Vinyl Dimethicone Crosspolymer and Silica	5.00	www.dowcorning.com
Magnesium Stearate	Magnesium Stearate	3.00	www.sigmaaldrich.com
Uniphén P-23	Phenoxyethanol (and) Methylparaben (and) Ethylparaben (and) Butylparaben	0.30	www.induchem.com
B			
Prestige® Soft Bronze	Mica (and) Iron Oxides	11.00	www.eckart.net
Prestige® Obsidian	Mica (and) Titanium Dioxide (and) Ferric Ferrocyanide (and) Carmine (and) Iron Oxides	11.00	www.eckart.net

Procedure

1. Mix phase A and heat up to 85°C
2. Pre-mix phase B
3. Add phase B to phase A while stirring
4. Pour into an appropriate container
5. Cool down to RT

Stability

Stable for at least 3 months at RT and 40°C.

Customer Support

ECKART GmbH & Co. KG
info.eckart@altana.com

ECKART Cosmetic Colours LLC
info.eckart.cosmetics@altana.com

ECKART Asia Limited
info.eckart.asia@altana.com

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.