

## Pressed Eye Shadow - 2008 Trend Color - "Raspberry Sorbet"

Color Cosmetics

Ref: CC/0320/EU

Product Name	INCI Name	%W/W	Supplier
<b>A</b>			
		100.00	
Silk Mica	Mica	17.00	www.vwr.com
Softouch CCS 102	Boron Nitride	2.50	www.advceramicscos.com
Talc Powder	Talc	23.50	www.riedelhaen.com
Kemilub EZ-V	Zinc Stearate	7.00	www.undesa.com
Prestige® Ruby	Mica (and) Titanium Dioxide (and) Carmine	13.00	www.eckart.net
Prestige® Soft Red	Mica (and) Titanium Dioxide	12.00	www.eckart.net
Prestige® Sparkling Silver	Mica (and) Titanium Dioxide	8.00	www.eckart.net
Prestige® Amethyst	Mica (and) Titanium Dioxide (and) Ferric Ferrocyanide (and) Carmine	4.00	www.eckart.net
Prestige® Bright Bronze	Mica (and) Titanium Dioxide	3.00	www.eckart.net
<b>B</b>			
Dow Corning® 200 Fluid 5 cst	Dimethicone	5.00	www.dowcorning.com
Dow Corning® 9040 Elastomer	Cyclomethicone (and) Dimethicone Crosspolymer	5.00	www.dowcorning.com

### Procedure

1. Mix phase A
2. Add phase B and stir until homogenous
3. Press eye shadow at 150 bar for 30 s

### Stability

Stable for at least 3 months at RT and 40°C.

### Customer Support

ECKART GmbH & Co. KG  
info.eckart@altana.com

ECKART Cosmetic Colours LLC  
info.eckart.cosmetics@altana.com

ECKART Asia Limited  
info.eckart.asia@altana.com

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.