

| | Date of impression page/of | 06.12.2024/18:15:23 1/1 | |
|--------------------------|----------------------------|----------------------------|--|
| | edition | 09.01.2024 | |
| STAPA IL HYDROLAN 2156 5 | 5900/G Alumi | nium Paste | |

material denomination material-no. material description

005362GD0 Pigmentpaste of flaky aluminiumpowder produced of pure aluminium min. 99,5 % EN 576, with an inorganic coating

Specific gravity app. 1,4 kg/l The solvent contained is isopropanol (IL) including lubricant and additives. Pigmentcomposition: aluminium app. 56% coating app. 4%

material specification

| insp. characteristic | specification | unit |
|--|---------------|------|
| TI00004 pigment content / non volatile | 58,0 - 62,0 | % |
| TI00004 volatile content | 38,0 - 42,0 | % |
| TI00005 sieving < 40 μm | 99,9 - 100,0 | % |
| TI00033 aqueous paint spray-out | pass | |
| TI00489 D 10 | 8,0 - 12,0 | μm |
| TI00489 D 50 | 17,0 - 23,0 | μm |
| TI00489 D 90 | 29,0 - 37,0 | μm |

total shelf life in month: 24

EC-safety data sheet-no. 005362GD0

The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

| Draft | Approval | Release |
|--------------------|------------|-----------------|
| Technical services | Production | Quality control |
| 09.01.2024 | 09.01.2024 | 09.01.2024 |

This document has been printed automatically and will not be signed.