

Preliminary Technical Product Information



PLATINSTAR UV LED 168 004 Shrink Silver

Article-No.:

028980..

Product Name:

PLATINSTAR UV LED 168 004 Shrink Silver

REVISION: 0

EDITION: AUG 2025

IDENT-NO.:00583.E

PAGE 1 OF 2

Product description:

PLATINSTAR UV/LED 168 004 Shrink Silver is a radical curing, solvent-free, stable one-component Flexo ink for shrinkable films based on aluminium pigments. The selection of photoinitiators makes the formulation suitable for both UV and LD curing. A new developed fine Aluminium pigment with "Platinum dollar" milling technology is used for PLATINSTAR UV/LED 168 silver to offer very high metallic effect by minimal ghosting or dulling even when the film shrinks.

During the curing process PLATINSTAR UV/LED 168 004 Shrink Silver may release odour-generating by-products and is neither low-migration nor low-odour. Therefore it might contain unevaluated substances with the potential to migrate. Further essential measures for food packaging inks like specific raw material selection, analytic control of raw materials and final products on composition and impurities, GMP production, can not be guaranteed for PLATINSTAR UV/LED 168 004 Shrink Silver. **Therefore ECKART does not generally recommend this ink series for the production of packaging for food, beverages and tobacco, without the customer proving suitability of this inks series for the specific application via a migration test or other measures (e.g. use of functional barriers in the packaging design).**

Application:

PLATINSTAR UV/LED 168 004 Shrink Silver is suitable for reverse print (second surface) flexo printing on films for shrink sleeve labelling. Over lacquering or backing, e. g. with white is recommended to avoid rubbing off on package surface during shrinkage and to preserve the metallic effect.

Product properties:

Curing speed:

PLATINSTAR UV/LED 168 004 Shrink Silver shows good and fast curing on many substrates, with using a UV-lamp capacity of 160 Watt/cm and printing speeds up to 90 m/min.

Rub resistance:

A backing ink (white or clear coating) is recommended for adequate rub and scratch resistance.

Adhesion:

PLATINSTAR UV/LED 168 004 Shrink Silver shows good adhesion on PETG, OPS and PVC. Corona treatment is recommended. The maximum adhesion takes effect after around 24 hours. Tests are necessary prior to any commercial use.

Organoleptic Properties (Taint and Odour):

PLATINSTAR UV/LED 168 004 Shrink Silver has been designed for use on secondary food packaging and packaging where a functional barrier exists between the primary packaging and the product.

In all cases the printed material / package should be tested to ensure that the organoleptic properties satisfy the packaging specification.

Migration:

PLATINSTAR UV/LED 168 004 Shrink Silver is not recommended for use on primary food packaging or in any other areas where low migration is an essential requirement. The product however can be used for secondary food packaging and applications that have appropriate barrier protection between the primary packaging and the product. In all cases the printed material / package should be tested to ensure that the migration properties satisfy the packaging specification.

Additional product properties:

PLATINSTAR UV/LED	168 004 Shrink Silver
Pigment content	approx. 8.0 %
Pigment size (D ₅₀)	approx. 9 µm
Solvent content	approx. < 1%

For specifications of our products, please refer to the technical data sheet.

Recommended printing parameters:

Anilox configuration:

For shrink sleeve applications, low ink film is recommended. The higher the ink film, the more change in colour will occur during shrinkage. The following configurations have shown to be useful:

	L/cm	L/inch	Volume cm ³ /m ²	Volume BCM
Full areas & coarse lines	80-120	200-300	9.3-12.4	6.0-8.0
Fine lines	140-170	360-440	7.7-10.8	5.0-7.0

Printing speed:

At 160 Watt/cm UV-lamp capacity and 9 cm³/m² Anilox volume a printing speed of 90 m/min can be achieved. Dependent on substrate, the printing speed varies.


Printing viscosity:

PLATINSTAR UV/LED 168 004 Shrink Silver is supplied with print viscosity.

Dilution:

The inks are already adjusted to printing viscosity. It's not recommended to add reactive diluents as a negative impact on shrinkage as well as on optical appearance, curing speed and stability of the ink could occur.

Cleaning recommendations:

Preliminary Technical Product Information			
PLATINSTAR UV LED 168 004 Shrink Silver			
Article-No.: 028980..		Product Name: PLATINSTAR UV LED 168 004 Shrink Silver	
REVISION: 0	EDITION: AUG 2025	IDENT-NO.: 00583.E	PAGE 2 OF 2

PLATINSTAR UV/LED inks can be cleaned by using conventional UV-cleaning agents. Also with esters or ester/alcohol mixtures the uncured inks can be removed easily from the cylinders.

Please refer to the safety data sheet and the safety guidelines given there.

Handling:

PLATINSTAR UV/LED inks are stable, brilliant one-component inks that can be printed without modification. Blending with other components should only be done on ECKART's recommendation in order to avoid a possible decrease in quality.

Metallic inks tend to settle because of the high specific gravity of the pigment. This is normal and not due to a lack of quality. The inks can be easily stirred up and homogenised again. This should be done before viscosity is checked. No pigment settling should be left on the bottom of the container.

When handling UV/LED curable inks please refer to the safety data sheet and the safety guidelines given there.

Storage and transportation:

PLATINSTAR UV/LED inks should be stored at temperatures below 25°C. Direct sunlight should also be avoided. High temperatures can lead to gelling. Low temperatures can result in the separation of low soluble binder components. Opened containers should never be handled in the direct sunlight, since this result in a preliminary polymerisation.

Shelf life: 6 months

Important: ECKART strongly recommends disposing of used ink after running on press, as the shelf-life of this material can be greatly reduced due to various factors such as light, heat, contaminants etc.

ECKART cannot guarantee the shelf life of printing ink which has been previously used or modified, nor for ink which has been stored out with the conditions above.

For further information or samples, please contact:

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Germany

mail: Info.eckart@altana.com

www.eckart.net

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.