

# Mousse Eye Shadow – “Big City Life”

Urban Connection  
Spring/Summer2023

Product Name	INCI Name	%W/W	Supplier
<b>A</b>			
TIXOGEL-CCT	Caprylic/Carpic Triglyceride (and) Stearalkonium Bentonite (and) Propylene Carbonate	30.00	www.eckart.net
CLAYTONE-VP V	Quaternium-90 Bentonite	2.50	www.eckart.net
DUB PTIS	Pentaerythrityl Tetraisostearate	5.00	www.stearinerie-dubois.com
Silmer G162-F	Cyclopentasiloxane (and) Dimethicone/Vinyl Dimethicone Crosspolymer (and) Perfluorononyl Dimethicone	10.00	www.siltech.com
Silmer QT9-30-CG	Polymethylsilsesquioxane (and) Isododecane	21.30	www.siltech.com
<b>B</b>			
SYNCRYSTAL Turquoise	Synthetic Fluorophlogopite (and) Titanium Dioxide (and) Iron Oxides (and) Ferric Ferrocyanide (and) Tin Oxide	20.30	www.eckart.net
SYNCRYSTAL Soft Black	Synthetic Fluorophlogopite (and) Iron Oxides	1.20	www.eckart.net
VISIONAIRE Sparkling Silver Sea	Synthetic Fluorophlogopite (and) Titanium Dioxide (and) Tin Oxide	8.50	www.eckart.net
<b>C</b>			
Euxyl K830	Phenoxyethanol, Ethylhexylglycerin* (and) Octenidine HCl	1.00	www.ashland.com
Angieberry	Fragrance	0.20	www.drom.com

#### Procedure:

1. Combine phase A and heat up to 80°C, mix until homogeneous
2. Add phase B to A and mix with medium shear until homogeneous
3. Cool down phase AB to 50°C
4. Add phase C and mix with medium shear
5. Pour into an appropriate container and let cool to RT



#### Stability:

Stable for at least 6 months at RT and 40°C  
Stable for at least 1 month at 50°C

#### Customer Support:

ECKART GmbH  
info.eckart@altana.com

ECKART America Corporation  
info.eckart.cosmetics@altana.com

ECKART Asia Limited  
info.eckart.asia@altana.com

This document does not constitute a legally binding obligation of Eckart. While the information contained herein and our technical advice – whether verbal, in writing or by way of trials – are given in good faith, it is provided for your guidance only. We recommend testing our products as to their suitability for your envisaged purpose prior to use. Furthermore, you are responsible for observing all laws and regulations relevant to any products mentioned herein and the products' application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.

Date: 01.09.2021  
Revision: 01.09.2021

# Mousse Eye Shadow – “Go Go Go Green”

Urban Connection  
Spring/Summer2023

Product Name	INCI Name	%W/W	Supplier
<b>A</b>			
TIXOGEL-CCT	Caprylic/Carpic Triglyceride (and) Stearalkonium Bentonite (and) Propylene Carbonate	30.00	www.eckart.net
CLAYTONE-VP V	Quaternium-90 Bentonite	2.50	www.eckart.net
DUB PTIS	Pentaerythryl Tetraisostearate	5.00	www.stearinerie-dubois.com
Silmer G162-F	Cyclopentasiloxane (and) Dimethicone/Vinyl Dimethicone Crosspolymer (and) Perfluorononyl Dimethicone	10.00	www.siltech.com
Silmer QT9-30-CG	Polymethylsilsesquioxane (and) Isododecane	21.30	www.siltech.com
<b>B</b>			
SYNCRYSTAL Green	Synthetic Fluorphlogopite (and) Titanium Dioxide (and) Tin Oxide	17.20	www.eckart.net
SYNCRYSTAL Sparkling Silver	Synthetic Fluorphlogopite (and) Titanium Dioxide (and) Tin Oxide	12.20	www.eckart.net
SunCroma FD&C Yellow 5 Al Lake C69-002	Yellow 5 Lake (CI 19140)	0.50	www.sunchemical.com
Spectra FD&C Blue 1 Alum Lake LL 5.FC.0010LL0	Blue 1 Lake (CI 42090)	0.10	www.spectracolors.com
<b>C</b>			
Euxyl K830	Phenoxyethanol, Ethylhexylglycerin* (and) Octenidine HCl	1.00	www.ashland.com
Angieberry	Fragrance	0.20	www.drom.com

#### Procedure:

- 1.Combine phase A and heat up to 80°C, mix until homogeneous
- 2.Add phase B to A and mix with medium shear until homogeneous
- 3.Cool down phase AB to 50°C
- 4.Add phase C and mix with medium shear
- 5.Pour into an appropriate container and let cool to RT



#### Stability:

Stable for at least 6 months at RT and 40°C

Stable for at least 1 month at 50°C

#### Customer Support:

ECKART GmbH  
info.eckart@altana.com

ECKART America Corporation  
info.eckart.cosmetics@altana.com

ECKART Asia Limited  
info.eckart.asia@altana.com

This document does not constitute a legally binding obligation of Eckart. While the information contained herein and our technical advice – whether verbal, in writing or by way of trials – are given in good faith, it is provided for your guidance only. We recommend testing our products as to their suitability for your envisaged purpose prior to use. Furthermore, you are responsible for observing all laws and regulations relevant to any products mentioned herein and the products' application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.

Date: 01.09.2021

Revision: 01.09.2021