

Date of impression 10.04.2024/08:56:35
page/of 1/2

edition 07.09.2022

material denomination **SYNCRYSTAL Soft Ivory**
material-no. 027374MJ0
material description Free flowing powder with a skin tone and pearly silver reflection color comprising plate-lets of synthetic fluorphlogopite *

material specification

insp. characteristic	specification	unit
visual and colorimetric evaluation	pass	
TI00127 D 50	8,0 - 11,0	µm
TI00154 total aerobic bacteria count	<= 100	cfu/g
TI00154 total yeast & mould count	<= 100	cfu/g
TI00027 titanium dioxide	28,0 - 37,0	%
TI00027 tin oxide	<= 1,0	%
TI00074 Pb	<= 0,0001	%
TI00074 Cd	<= 0,0001	%
TI00075 Sb	<= 0,0001	%
TI00075 As	<= 0,0001	%
TI00075 Hg	<= 0,0001	%
TI00247 pH of 10% aqueous suspension	5,0 - 10,0	
TI00147 synthetic fluorphlogopite	56,0 - 70,0	%
TI00076 Ba	<= 0,0010	%
TI00076 Co	<= 0,0010	%
TI00076 Cr	<= 0,0010	%
TI00076 Cu	<= 0,0010	%
TI00076 Ni	<= 0,0010	%
TI00076 Zn	<= 0,0010	%
TI00027 iron oxide	2,0 - 6,0	%
TI00000 pathogens	absent	

total shelf life in month: 120

EC-safety data sheet-no. 027374MJ0

Other remarks:

INCI name	CI No.	CAS No.	EINECS No.
synthetic fluorphlogopite		12003-38-2	234-426-5
titanium dioxide	77891	13463-67-7	236-675-5
iron oxides	77491	1309-37-1	215-168-2
tin oxide		18282-10-5	242-159-0

We confirm that the raw material is in consistence with the relevant European Cosmetics Directives and the US Government regulations as specified in 21 CFR for all intended cosmetic uses of the ingredient.

The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

technical data sheet

Draft

Technical services

07.09.2022

Approval

Production

07.09.2022

Release

Quality control

07.09.2022

This document has been printed automatically and will not be signed.