



silverdream®

Visionaire®

Metallic effects for  
solvent-borne nail  
polishes

A member of  ALTANA

 **ECKART**  
Effect Pigments



## Metallic effects for solvent-borne nail polishes

SILVERDREAM is dedicated to metallic pigment preparations for nail polishes. Besides standing out by luxurious and valorizing metallic look, the pigment preparations unfold additional attractiveness when combined with pearlescent pigments like MIRAGE or SYNCRYSTAL as well as colorants.

The Silverdream product line features impressive metallic highlights like Starlight, which represents captivating silver sparkle or Prismatic types, unique products made by PVD technology with outstanding rainbow-like appearance.

Silverdream Polaris – applied in combination with a special magnet – exhibits extra-ordinary three-dimensional effects thanks to the alignment of the iron flakes incorporated by magnetic forces.

VISIONAIRE shades are synonyms for superior performance, dramatic metallic reflection and excellent coverage.

silverdream®

Visionaire®



<b>SILVERDREAM</b>	Article No.	Particle Size (microns)
Type		
<b>Metallic pigment preparations</b>		
Starlight 70 IL	007302	20 – 95
Polaris 90 WM	052329	5 – 40
Type		
<b>Aluminum pigment dispersions</b>		
L-55350	056252ZZ268	11 – 12
Prismatic H-50720	022357ZZ168	18 – 22
Prismatic H-50550	052506ZZ168	48 – 52
Prismatic H-115002	053002ZZ168	100 – 150

<b>VISIONAIRE</b>	Article No.	Particle Size (microns)
Type		
<b>Silver shades</b>		
Splendid Silver Sea	022686	5 – 50
Bright Silver Sea	040443	15 – 70
Sparkling Silver Sea	040966	20 – 95
<b>Special shades</b>		
Bright Splendid Red 34	041711	15 – 70
Bright Splendid Champagne	021094	15 – 70

Content (%)			
Aluminum Powder (CI 77000) CAS: 7429-90-5 EINECS: 231-072-3	Iron Powder CAS: 7439-89-6 EINECS: 231-096-4	Isopropyl Alcohol CAS: 67-63-0 EINECS: 200-661-7	Paraffinum Liquidum CAS: 8042-47-5 EINECS: 232-455-8
68 – 72	–	28 – 32	–
–	88 – 92	–	8 – 12
	Ethyl Acetate CAS: 141-78-6 EINECS: 205-500-4	Acetone CAS: 67-64-1 EINECS: 200-662-2	Butyl Acetate CAS: 123-86-4 EINECS: 204-658-1
10	< 90	< 3	–
7	< 95	< 6	–
5	< 95	< 9	–
0.4 – 1.8	–	10 – 50	50 – 90

Content (%)			
Aluminum Powder (CI 77000) CAS: 7429-90-5 EINECS: 231-072-3	Silica CAS: 7631-86-9 EINECS: 231-545-4	Red 34 (CI 15880) CAS: 6417-83-0 EINECS: 229-142-3	Aluminum Hydroxide CAS: 21645-51-2 EINECS: 244-492-7
85 – 95	5 – 15		
85 – 95	5 – 15		
85 – 95	5 – 15		
75 – 83	13 – 17	4 – 8	–
58 – 73	5 – 10	–	22 – 32

## Metallic pigment preparations



**Starlight 70 IL**

20 – 95  $\mu\text{m}$

Article No. 07302



**Polaris 90 WM**

(Example of Application)

5 – 40  $\mu\text{m}$

Article No. 052329

## Special shades



**Bright Splendid Red 34** 15-70 µm Article No. 041711



**Bright Splendid Champagne** 15-70 µm Article No. 021094





**L-55350**

11 – 12  $\mu\text{m}$

Article No. 056252ZZ268



**Prismatic H-50720**

18 – 22  $\mu\text{m}$


Article No. 022357



**Prismatic H-50550**

48 – 52  $\mu\text{m}$

Article No. 052506ZZ168



**Prismatic H-115002**

100 – 150  $\mu\text{m}$

Article No.



## Silver shades



**Splendid Silver Sea**      5 – 50  $\mu\text{m}$       Article No. 022686



**Bright Silver Sea**      15 – 70  $\mu\text{m}$       Article No. 040443



**Sparkling Silver Sea**      20 – 95  $\mu\text{m}$       Article No. 040966



# ECKART

Effect Pigments

ECKART GmbH  
Guentersthal 4  
91235 Hartenstein, Germany  
Tel +49 9152 77-0  
Fax +49 9152 77-7008  
info.eckart@altana.com  
www.eckart.net

ECKART America Corporation  
830 East Erie Street  
Painesville, Ohio 44077, USA  
Tel +1 440 954 7600  
Fax +1 440 354 6224  
Toll-free 866 458 7837  
info.eckart.cosmetics@altana.com  
www.eckart.net

ECKART Asia Ltd.  
Unit 3706-08, 37/F, Sunlight Tower  
248 Queen's Road East  
Wan Chai, Hong Kong  
Tel +852 3102 7200  
Fax +852 2882 5366  
info.eckart.asia@altana.com  
www.eckart.net

2/July2017.2 COS  
099174XX0

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.