

Pressed Eye Shadow - "Louisiana Iris"

You + Me

Spring/Summer 2019

Product Name	INCI Name	%W/W	Supplier
A			
SYNAFIL S1050	Synthetic Fluorphlogopite	16.00	www.eckart.net
Talc Powder	Talc	25.00	www.vwr.com
Agenaflo OS 9051	Aluminium Starch Octenylsuccinate	8.00	www.agrana.com
SYNCRYSTAL Silver	Synthetic Fluorphlogopite (and) Titanium Dioxide (and) Tin Oxide	10.00	www.eckart.net
SYNCRYSTAL Red	Synthetic Fluorphlogopite (and) Titanium Dioxide (and) Tin Oxide	10.00	www.eckart.net
SYNCRYSTAL Blue	Synthetic Fluorphlogopite (and) Titanium Dioxide (and) Tin Oxide	10.00	www.eckart.net
Manganese Violet (CI 77742)	Manganese Violet	7.00	
B			
Xiameter PMX-0345 Cyclosiloxane	Cyclomethicone	4.00	www.dowcorning.com
Ewalan IP	Isopropyl Lanolate	6.00	www.wagnerlanolin.de
Ceraphyl 847	Octyldodecyl Stearoyl Stearate	4.00	www.ashland.com

Procedure:

1. Weigh in phase A
2. Add phase B and stir until homogeneous
3. Press eye shadow at 100bar for 30s



Customer Support:

ECKART GmbH
info.eckart@altana.com

ECKART America Corporation
info.eckart.cosmetics@altana.com

ECKART Asia Limited
info.eckart.asia@altana.com

This document does not constitute a legally binding obligation of Eckart. While the information contained herein and our technical advice – whether verbal, in writing or by way of trials – are given in good faith, it is provided for your guidance only. We recommend testing our products as to their suitability for your envisaged purpose prior to use. Furthermore, you are responsible for observing all laws and regulations relevant to any products mentioned herein and the products' application. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties.

Date: 22.02.2017
Revision: 22.02.2017