STAPA

005735HV0



| | Date of impression page/of | on 09.04.2024/14:12:07 1/1 |
|--------------------|----------------------------|-------------------------------|
| | edition | 09.01.2024 |
| IL HYDROLAN 701 55 | 5900/G Alum | inium Paste |

Pigmentpaste of flaky aluminiumpowder produced of pure aluminium min. 99,5 % EN 576, with an inorganic coating Specific gravity app. 1,4 kg/l The solvent contained is isopropanol (IL) including lubricant and

material specification

material denomination

material description

material-no.

| insp. characteristic | specification | unit |
|--|---------------|------|
| TI00004 pigment content / non volatile | 58,0 - 62,0 | % |
| TI00004 volatile content | 38,0 - 42,0 | % |
| Tl00005 sieving < 63 μm | 99,9 - 100,0 | % |
| TI00033 aqueous paint spray-out | pass | |
| TI00489 D 10 | 5,0 - 9,0 | μm |
| TI00489 D 50 | 17,0 - 23,0 | μm |
| TI00489 D 90 | 37,0 - 45,0 | μm |

total shelf life in month: 24

EC-safety data sheet-no. 005735HV0

The Data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

Draft Technical services 09.01.2024 Approval Production 09.01.2024 Release Quality control 09.01.2024

This document has been printed automatically and will not be signed.