

Date of impression 09.04.2024/14:12:48

page/of

edition 09.01.2024

material denomination

STAPA BG HYDROLAN 501 55900/G Aluminium Paste

material-no.

005847GK0

material description

Pigmentpaste of flaky aluminiumpowder produced of pure aluminium min. 99,5 % EN 576, with an inorganic coating

Specific gravity app. 1,4 kg/l

The solvent contained is butyl glykol (BG) including lubricant and

material specification

insp. characteristic	specification	unit
TI00004 pigment content / non volatile	58,0 - 62,0	%
TI00004 volatile content	38,0 - 42,0	%
TI00005 sieving < 63 µm	99,9 - 100,0	%
TI00033 aqueous paint spray-out	pass	
TI00489 D 10	8,0 - 12,0	μm
TI00489 D 50	23,0 - 29,0	μm
TI00489 D 90	44,0 - 52,0	μm

total shelf life in month: 24

EC-safety data sheet-no. 005847GK0

The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

DraftApprovalReleaseTechnical servicesProductionQuality control09.01.202409.01.202409.01.2024

This document has been printed automatically and will not be signed.