

	Date of impression page/of	09.04.2024/14:00:35 1/1	
	edition	09.01.2024	
STAPA BG HYDROLAN 2154	Aluminium Pa	ste	

007497GD0 Pigmentpaste of flaky aluminiumpowder produced of pure aluminium min. 99,5 % EN 576, with an inorganic coating

Specific gravity app. 1,4 kg/l The solvent contained is butyl glykol (BG) including lubricant and additives. Pigmentcomposition: aluminium app. 56% coating app. 4%

## material specification

material denomination

material description

material-no.

specification	unit
58,0 - 62,0	%
38,0 - 42,0	%
99,9 - 100,0	%
pass	
9,0 - 13,0	μm
18,0 - 24,0	μm
31,0 - 39,0	μm
	58,0 - 62,0 38,0 - 42,0 99,9 - 100,0 pass 9,0 - 13,0 18,0 - 24,0

total shelf life in month: 24

EC-safety data sheet-no. 007497GD0

The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

Draft	Approval	Release
Technical services	Production	Quality control
09.01.2024	09.01.2024	09.01.2024

This document has been printed automatically and will not be signed.