

Date of impression 09.04.2024/14:32:52

page/of 1/1

edition

09.01.2024

material denomination

material description

STAPA IL HYDROLAN S 2100 Aluminium Paste

material-no. 051994HV0

Pigmentpaste of flaky aluminiumpowder produced of pure

aluminium min. 99,5 % EN 576, with an inorganic coating

Specific gravity app. 1,4 kg/l

The solvent contained is isopropanol (IL) including lubricant and

additives.

Pigmentcomposition: aluminium app. 54% coating app. 6%

material specification

| insp. characteristic | specification | unit |
|--|---------------|------|
| TI00004 pigment content / non volatile | 58,0 - 62,0 | % |
| Tl00004 volatile content | 38,0 - 42,0 | % |
| TI00005 sieving < 40 µm | 99,9 - 100,0 | % |
| TI00033 aqueous paint spray-out | pass | |
| TI00489 D 10 | 11,0 - 15,0 | μm |
| TI00489 D 50 | 21,0 - 27,0 | μm |
| TI00489 D 90 | 35,0 - 43,0 | μm |

total shelf life in month: 24

EC-safety data sheet-no. 051994HV0

The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

Draft Approval Release

Technical services Production Quality control

09.01.2024 09.01.2024 09.01.2024

This document has been printed automatically and will not be signed.