

Date of impression 10.04.2024/09:31:47

page/of

1/2

edition

16.07.2021

SYNCRYSTAL Jade material denomination

material-no. 035676MJ0

Free flowing green powder comprising plateletes of synthetic material description

fluorphlogopite coated with titanium dioxide, ferric ferrocyanide

iron oxides and small amounts of tin oxide.

## material specification

| insp. characteristic                   | specification | unit  |
|--|---------------|-------|
| visual and colorimetric evaluation     | pass          |       |
| TI00127 D 50                           | 18,0 - 23,0   | μm    |
| TI00154 total aerobic bacteria count   | <= 100        | cfu/g |
| TI00154 total yeast & mould count      | <= 100        | cfu/g |
| TI00027 titanium dioxide               | 53,0 - 67,0   | %     |
| TI00027 tin oxide                      | <= 1,0        | %     |
| TI00074 Pb                             | <= 0,0001     | %     |
| TI00074 Cd                             | <= 0,0001     | %     |
| TI00075 Sb                             | <= 0,0001     | %     |
| TI00075 As                             | <= 0,0001     | %     |
| TI00075 Hg                             | <= 0,0001     | %     |
| TI00147 ferric ferrocyanide (CI 77510) | 3,0 - 5,0     | %     |
| TI00247 pH of 10% aqueous suspension   | 3,0 - 8,0     |       |
| TI00147 synthetic fluorphlogopite      | 25,0 - 43,0   | %     |
| TI00076 Ba                             | <= 0,0010     | %     |
| TI00076 Co                             | <= 0,0010     | %     |
| TI00076 Cr                             | <= 0,0010     | %     |
| TI00076 Cu                             | <= 0,0010     | %     |
| TI00076 Ni                             | <= 0,0010     | %     |
| TI00076 Zn                             | <= 0,0010     | %     |
| TI00000 pathogens                      | absent        |       |
| TI00147 iron oxides                    | 1,0 - 2,0     | %     |

total shelf life in month: 36

EC-safety data sheet-no. 035676MJ0

Other remarks:

| INCI name                 | CI No. | CAS No.    | EINECS No. |
|---------------------------|--------|------------|------------|
| synthetic fluorphlogopite |        | 12003-38-2 | 234-426-5  |
| titanium dioxide          | 77891  | 13463-67-7 | 236-675-5  |
| iron oxides               | 77492  | 51274-00-1 | 257-098-5  |
| ferric ferrocyanide       |        | 14038-43-8 | 237-875-5  |
| tin oxide                 |        | 18282-10-5 | 242-159-0  |

Pigment is unstable to alkaline, strong acids and some salts.

We confirm that the raw material is in consistence with the relevant European Cosmetics Directives and the US Government regulations as specified in 21 CFR for all intended cosmetic uses of the ingredient.

The Data on this technical information sheet correspond with the current status of our knowledge and experience.



ECKART GMBH Güntersthal 4, 91235 Hartenstein Tel +49 9152 77-0, Fax +49 9152 77-0 info.eckart@altana.com, www.eckart.net



## technical data sheet

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

DraftApprovalReleaseTechnical servicesProductionQuality control16.07.202116.07.202116.07.2021

This document has been printed automatically and will not be signed.

