

	Date of impression page/of	09.04.2024/14:11:57 1/1
	edition	09.01.2024
STAPA IL HYDROLAN 9160 5 005701HV0 Pigmentpaste of flaky aluminiumpowder produced o		nium Paste

Pigmentpaste of flaky aluminiumpowder produced of pure aluminium min. 99,5 % EN 576, with an inorganic coating

Specific gravity app. 1,4 kg/l The solvent contained is isopropanol (IL) including lubricant and additives. Pigmentcomposition: aluminium app. 56% coating app. 4%

material specification

material denomination

material description

material-no.

insp. characteristic	specification	unit
TI00004 pigment content / non volatile	58,0 - 62,0	%
TI00004 volatile content	38,0 - 42,0	%
TI00005 sieving < 63 μm	99,9 - 100,0	%
TI00033 aqueous paint spray-out	pass	
TI00489 D 10	3,0 - 7,0	μm
TI00489 D 50	11,0 - 17,0	μm
TI00489 D 90	25,0 - 31,0	μm

total shelf life in month: 24

EC-safety data sheet-no. 005701HV0

The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

Draft	Approval	Release
Technical services	Production	Quality control
09.01.2024	09.01.2024	09.01.2024

This document has been printed automatically and will not be signed.