


Technical Product Information			
ROTOVARIO UV FPG 950 204 Silver			
Article-No.: 022190...		Product Name: ROTOVARIO UV FPG 950 204 Silver	
REVISION: 1	EDITION: JUNE 2021	IDENT-No.: 00442.E	PAGE 1 OF 2

Low migration UV Silver paste for the formulation of UV Flexo and Offset printing inks.

Product description:

ROTOVARIO UV FPG 950 204 Silver contains stabilized, leafing aluminium pigment pasted in acrylate monomer (TMP(EO)TA) for the formulation of stable, radical curing, one-component UV Flexo and Offset printing inks for food packaging application.

- All ingredients are either low migration or meet the specific migration limits for evaluated substances under selected test conditions.
- Raw materials are selected with preference for high purity materials.
- White spirit and mineral oil are excluded from the production process of this aluminium paste.
- GMP compliant production of ROTOVARIO UV FPG 950 204 Silver (minimized risk of cross contamination) is guaranteed.
- The formulation is specifically developed for food packaging application; under selected test conditions migration limits are undercut.

The above fundamentally differentiates ROTOVARIO UV FPG 950 204 Silver from standard UV Silver pastes.

ROTOVARIO UV FPG 950 204 silver paste is not suitable for formulating inks for direct food contact

Organoleptic properties (taint and odour):

In all cases the printed material / package has to be tested to ensure that the organoleptic properties satisfy the packaging specification.

Application:

ROTOVARIO UV FPG 950 204 Silver paste is suitable for formulating UV curing Flexo printing inks on paper, board and foil for the manufacturing of food packaging (indirect contact).

As with all metallic inks the substrate has a big influence on the final result with respect to effect, cure and adhesion. Very absorbent or uneven substrates often cause poor pigment orientation resulting in inferior brilliance. In some cases, the use of primers for an improvement of the substrate surface is advantageous.

In order to provide the maximum level of metallic brilliance ROTOVARIO UV FPG 950 204 Silver is based on leafing aluminium pigments, which could limit overprintability of the finished ink. However, dependent on formulation, printing parameters and substrate, metallic UV printing inks will accept many different types of overprinting including Thermal Transfer, Hot Foil Stamping, In-Line and Off-Line overvarnishing. It's recommended to cure the metallic ink before the UV varnish is applied, to achieve optimum results.

Please test the finished inks for overprintability prior to production runs.

Product properties:

The aluminium pigment of ROTOVARIO UV FPG 950 204 Silver gives a high metallic effect and transfers very well in finished UV curing inks.

Rub resistance:

ROTOVARIO UV FPG 950 204 Silver is based on a leafing metallic pigment to provide an ink with the highest level of metallic brilliance possible. Due to the leafing character of the aluminium pigments the finished ink may exhibit poor rub resistance (depending on the film weight, the substrate used and the printing speed applied).

Technical data:

ROTOVARIO UV	FPG 950 204 Silver
Pigment content	appr. 48%
Pigment size (D₅₀)	appr. 4,4 µm
Solvent content	< 0,2%
VOC	< 0,2%
TMP(EO)TA	appr. 43%

For specifications of our products, please refer to the technical data sheet.

Handling:

ROTOVARIO UV pastes are concentrates suitable for the formulation of UV curing Flexo printing inks. The pastes can be dispersed in a UV letdown by applying low shear forces.

When handling UV- products, please refer to the safety data sheet and the safety guidelines given there.


Cleaning recommendations:

ROTOVARIO UV products can be cleaned by using conventional UV cleaning agents. Also with esters or ester/alcohol mixtures the uncured inks can be removed easily from the cylinders. Please refer to the safety data sheet and the safety guidelines given.

Storage and transportation:

ROTOVARIO UV FPG concentrates should be stored at temperatures between 20°C and 25°C. Direct sunlight should also be avoided.

High temperatures can lead to gelling. Opened containers should never be exposed to direct sunlight, since this will result in a preliminary polymerisation.

Technical Product Information			
ROTOVARIO UV FPG 950 204 Silver			
Article-No.: 022190...		Product Name: ROTOVARIO UV FPG 950 204 Silver	
REVISION: 1	EDITION: JUNE 2021	IDENT-No.: 00442.E	PAGE 2 OF 2

Shelf life: 6 months

Important: The shelf life of the material can be greatly reduced due to various factors such as light, heat, contaminants etc. ECKART cannot guarantee the shelf life of products which have not been stored at the recommended conditions above.

For further information or samples, please contact:

ECKART GmbH
Güntersthal 4
91235 Hartenstein
Germany

mail: Info.eckart@altana.com

www.eckart.net

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.