

## Technical Data

### Zinc Flake Spray

*for indoors and outdoors applications*

Technical details Paint		Advice for handling	
colour shade	bright zinc	application temperature	ideal at approx. +18-25 °C
degree of gloss	metallic mat	surface preparation	clean, dry, free of grease and rust
base of binder	alkyd resin	primer	-----
base of pigment	Zinc/Aluminium	touch dry at + 20 °C	after approx. 30 minutes
temperature stability	bis ca. +240 °C	fully hardened	after approx. 10-12 hours
flash point	below +21 °C	recoat	after approx. 12 hours
Danger class	acc. to TRG 300		
hazard identification	Danger! Please see MSDS	authorisation acc. to guideline: 2004/42 EG	categorie "B/e" Specialpaints VOC max. 840 g/l (2007).
Propellant agent	Dimethylether	this product contains:	< 840 g/l VOC
storage	cool and dry		

Test results	
Cross cut test DIN 53151 / ISO 2409	GT 0 - 1
salt spray test ISO 9227	~ 550 hours (after 14 days dry storage before testing)
Humidity test DIN 50017	~ 180 hours (after 14 days dry storage before testing)
Bend test 5 mm	<input checked="" type="checkbox"/>
Resistant to oil and petrol (regular)	<input type="checkbox"/>
UV-durable	<input type="checkbox"/>
Film thickness	40 µm

Product features
Primer as cold galvanizing, long term corrosion protection abrasion resistant Spot weldable

Applications
Suitable for repairing damaged and rusty galvanised parts Excellent metal primer Can also be used as a topcoat

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.  
The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.  
We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:  
ECKART GmbH / Güntersthal 4 / 91235 Hartenstein / Germany  
Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com