

Technical Data

Heat Resistant Spray black

For indoor and outdoor applications

Technical details SPRAY		Advice for handling	
Colour shade	black	Application temperature	ideal at approx. +18 - 25 °C
Degree of gloss	mat	Surface preparation	clean, dry, free of grease and rust
Base of binder	silicone resin	Primer	if necessary with ECKART zinc dust*
Base of pigment	black pigment	Touch dry at +20 °C	after approx. 30 min.
Temperature stability	up to + 500 °C	Fully hardened	after stoving for 30 min. at 240 °C
Flash point/aerosol paint	below +21 °C	Recoat	---
Danger class	acc. to TRG 300		* up to 400 °C
Marking	Danger! Please see MSDS		
Propellant agent	propane/butane	Categorisation according to VOC directive: 2004/42 EG	Category "B/e" specialties VOC max. 840 g/l (2007).
Storage	cool and dry; acc. to TRG 300	This product contains:	< 840 g/l VOC

Test results

Cross cut test DIN 53151 / ISO 2409	GT 0-1
Salt spray test ISO 9227	---
Humidity test DIN 50017	---
T-bend test 5 mm	---
UV-durable	---
Minimum Film thickness	approx. 20 µm

Product features

Rust resistant in combination with a primer
 Weather resistant
 Wipe and touch resistant after stoving at +240 °C for 30 min.

Applications

Suitable for engine parts, exhaust systems, oven pipes, grills etc.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.
 The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.
 We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:
 ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany
 Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com