

## Technical Data

### Metallic Spray Deco Silver

For indoor applications

Technical details SPRAY		Advice for handling	
Colour shade	silver	Application temperature	ideal at approx. +18 - 25 °C
Degree of gloss	metallic gloss	Surface preparation	clean, dry, free of grease and rust
Base of binder	natural resin	Primer	-----
Base of pigment	aluminium	Touch dry at +20 °C	after approx. 10 min.
Temperature stability	up to approx. + 80 °C	Fully hardened	after approx. 10-12 hours
Flash point/aerosol paint	below + 21 °C	Recoat	-----
Danger class	acc. to TRG 300		
Marking	Danger! Please see MSDS		
Propellant agent	propane/butane	Category "B/e" specialties	VOC max. 840 g/l (2007).
Storage	cool and dry, acc. to TRG 300	This product contains:	< 840 g/l VOC

#### Test results

Cross cut test DIN 53151 / ISO 2409  
 Salt spray test ISO 9227  
 Humidity test DIN 50017  
 T-bend test 5 mm  
 UV-durable  
 Minimum Film thickness

} for deco products (interior applications) not relevant  
 approx. 10 µm

#### Product features

Brilliant gloss  
 High opacity  
 Quick drying  
 Good adhesion  
 not suitable for mechanical load

#### Applications

Ideal for frames, room and table decorations and much more  
 Suitable for metal, plastic, wood and other natural material.  
 Not for mechanically stressed objects, such as handrail or similar.

For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.  
 The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.  
 We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:  
 ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany  
 Tel.: ++ 49-(0)9152-77 0 / Fax: ++49-(0)9152-77 4435 / E-mail: info.eckart@altana.com