

Technical Data

Metallic Spray Deco Gold

For indoor applications

Technical details SPRAY		Advice for handling	
Colour shade	rich pale gold / brass	Application temperature	ideal at approx. +18 - 25 °C
Degree of gloss	metallic gloss	Surface preparation	clean, dry, free of grease and rust
Base of binder	synthetic resin	Primer	-----
Base of pigment	copper/zinc	Touch dry at +20 °C	after approx. 10 min.
Temperature stability	up to + 60 °C	Fully hardened	after approx. 10-12 hours
Flash point/aerosol paint	below + 21 °C	Recoat	-----
Danger class	acc. to TRG 300	Categorisation according to VOC directive: 2004/42 EG	
Marking	Danger! Please see MSDS	Category "B/e" specialties VOC max. 840 g/l (2007).	
Propellant agent	propane/butane	This product contains: < 840 g/l VOC	
Storage	cool and dry; acc. to TRG 300		

Test results

Cross cut test DIN 53151 / ISO 2409
 Salt spray test ISO 9227
 Humidity test DIN 50017
 T-bend test 5 mm
 UV-durable
 Minimum Film thickness

} for deco products (interior applications) not relevant
 approx. 15 µm

Product features

Brilliant gloss gold effect
 High opacity
 Quick drying
 Good adhesion
 not suitable for mechanical load

Applications

Ideal for frames, room and table decorations and much more
 Suitable for metal, plastic, wood and other natural material.
 Not for mechanically stressed objects, such as handrail or similar.
 For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.
 We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany
 Tel.: ++ 49-(0)9152-77 0 / Fax: ++49-(0)9152-77 4435 / E-mail: info.eckart@altana.com