

## Technical Data

# Clear Coat Spray

For indoor and outdoor applications

Technical details SPRAY		Advice for handling	
Colour shade	clear	Application temperature	ideal at approx. +18 - 25 °C
Degree of gloss	brilliant	Surface preparation	clean, dry, free of grease and rust
Base of binder	acrylic resin	Primer	-----
Base of pigment	-----	Touch dry at +20 °C	after approx. 30 min.
Temperature stability	up to +200°C /short time up to +300°C	Fully hardened	after approx. 10-12 hours
Flash point/aerosol paint	below +21 °C	Recoat	-----
Danger class	acc. to TRG 300		
Marking	Danger! Please see MSDS		
Propellant agent	propane/butane	Category "B/e" specialties VOC max.	840 g/l (2007).
Storage	cool and dry; acc. to TRG 300	VOC directive: 2004/42 EG	< 840 g/l VOC
		This product contains:	< 840 g/l VOC

### Test results

Cross cut test DIN 53151 / ISO 2409	GT 0
Salt spray test ISO 9227	--
Humidity test DIN 50017	--
T-bend test 5 mm	i.O.
UV-durable	140 h
Minimum Film thickness	approx. 25 µm

### Product features

Transparent glossy effect  
Wipe resistant  
Touch to dry  
Good adhesion  
durabel free from yellowing

### Applications

E. g. glossy finish for handicrafts, sealing of surfaces  
Ideal as anti-tarnish protection for non-ferrous metals such as copper, brass etc.  
Suitable for metal, wood, ceramics, glass and natural materials.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.  
We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany

Tel.: ++ 49-(0)9152-77 0 / Fax: ++49-(0)9152-77 4435 / E-mail: info.eckart@altana.com