

## Technical Data

# Zinc Alu Spray

*For interior and exterior use*

Technical details SPRAY		Advice for handling	
colour shade	bright zinc	Application temperature	ideal at ~ +18-25 °C
gloss	metallic glossy	substrate	clean, dry, free of grease and rust
binder	alkyd resin combination	Primer	--
pigment	Zinc- and Aluminiumflakes	Touch dry at +20 °C	after ~ 30 minuts
temperature stability	up to ~ +250 °C	Fully hardened	after ca. 10-12 Stunden
flashpoint/ Aerosol paint	below +21 °C	Recoat	after ca. 12 Stunden
dangerclass	acc.to TRG 300 Aerosol	authorisation acc. to guideline: 2004/42 EG	categorie "B/e" Specialpaints VOC max. 840 g/l (2007).
marking	Danger! Please see MSDS	this product contains:	< 840 g/l VOC
propellant	propane/butane		
storage	cool and dryn; acc.to TRG 300 Aerosole		

test results			
Cross cut test DIN 53151 / ISO 2409	GT 0 - 1		
salt spray test DIN EN ISO 72 53	~ 200 hours	(after 14 days dry storage before testing)	
Humidity test DIN 50017	--		
T-bend test 5 mm	ok		
UV-durable	--		
Minimum film thickness	40 µm		

features
cold-galvanizing
rust prevention
wipe resistant
spot weldable

application
Suitable for repairing damaged and rusty galvanised parts

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.  
The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.  
We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:  
ECKART GmbH / Güntersthal 4 / 91235 Hartenstein / Germany  
Tel.:++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com