

Technical Data

Zinc Dust Spray L

Technical details SPRAY		Advice for handling	
Colour shade	zinc grey	Application temperature	ideal at approx. +18 - 25 °C
Degree of gloss	mat	Surface preparation	clean, dry, free of fat and rust
Base of binder	alkyd resin	Primer	-----
Base of pigment	zinc dust	Touch dry at +20 °C	after approx. 15 min.
Temperature stability	up to approx. +300 °C	Fully hardened	after approx. 10-12 hours
Flash point/aerosol paint	below +21 °C	Recoat	after approx. 12 hours
Danger class	acc. to TRG 300		
Marking	Danger! Please see MSDS		
Propellant agent	Dimethylether	Categorisation according to VOC directive: 2004/42 EG	Category "B/e" specialties VOC max. 840 g/l (2007).
Storage	cool and dry; acc. to TRG 300	This product contains:	< 840 g/l VOC

Test results

Cross cut test DIN 53151 / ISO 2409	GT 1
Salt spray test ISO 9227	300 hours
Humidity test DIN 50017	240 hours
T-bend test 5 mm	<input checked="" type="checkbox"/>
UV-durable	---
Minimum Film thickness	75 µm

Product features

Anticorrosive primer as cold galvanizing
Rust resistant
Spot weldable

Applications

Suitable as optimal rust inhibitive primer for metal structures e.g. railings, fences, automobile parts, poles etc.
For priming as cold galvanizing.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.
The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.
We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Güntersthal 4 / 91235 Hartenstein / Germany

Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com