

## Technical Data Sheet

# Alu Spray glossy

*For indoor applications*

Technical details SPRAY		Advice for handling	
<b>Colour shade</b>	silver	<b>Application temperature</b>	ideal at approx. +18 - 25 °C
<b>Degree of gloss</b>	metallic high gloss	<b>Surface preparation</b>	clean, dry, free of grease and rust
<b>Base of binder</b>	hydrocarbon resin	<b>Primer</b>	----
<b>Base of pigment</b>	special aluminium	<b>Touch dry at +20 °C</b>	after approx. 10 min.
<b>Temperature stability</b>	up to approx. +400 °C	<b>Fully hardened</b>	after approx. 10-12 hours
<b>Flash point/aerosol paint</b>	below +21 °C	<b>Recoat</b>	No (because of mirror effect)
<b>Danger class</b>	acc. to TRG 300		
<b>Marking</b>	Danger! Please see MSDS		
<b>Propellant agent</b>	propane/butane	<b>Categorisation according to VOC directive: 2004/42 EG</b>	Category "B/e" specialties VOC max. 840 g/l (2007).
<b>Storage</b>	cool and dry; acc. to TRG 300	<b>This product contains:</b>	< 840 g/l VOC

### Test results

Cross cut test DIN 53151 / ISO 2409	} for deco products (interior applications) not relevant
Salt spray test ISO 9227	
Humidity test DIN 50017	
T-bend test 5 mm	
UV-durable	
Minimum Film thickness	

### Product features

Very brilliant, mirror-like gloss  
 High opacity  
 Quick drying  
 Good adhesion  
 Not for mechanically stressed objects

### Applications

Especially for artistic and decorative design elements e.g. for trade shows, samples, visual enhancement, creative handicrafts.

Suitable for metal and most of the common plastics.

Not for mechanically stressed objects such use handrail or similar

For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.

We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Güntersthal 4 / 91235 Hartenstein / Germany

Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com