

## Technical Data

### Alu Spray mat

For indoor and outdoor applications

Technical details SPRAY		Advice for handling	
<b>Colour shade</b>	silver satin	<b>Application temperature</b>	idealt at approx. +18 - 25 °C
<b>Degree of gloss</b>	metallic silver	<b>Surface preparation</b>	clean, dry, free of grease and rust
<b>Base of binder</b>	alkyd / acrylic resin	<b>Primer</b>	if necessary, ECKART Zinc Spray
<b>Base of pigment</b>	aluminium	<b>Touch dry at +20 °C</b>	after approx. 20 min.
<b>Temperature stability</b>	up to approx. +250 °C	<b>Fully hardened</b>	after approx. 8 hours
<b>Flash point/aerosol paint</b>	below +21 °C	<b>Recoat</b>	after approx. 6 - 8 hours
<b>Danger class</b>	acc. to TRG 300		
<b>Marking</b>	Danger! Please see MSDS		
<b>Propellant agent</b>	propane/butane	<b>Categorisation according to VOC directive: 2004/42 EG</b>	Category "B/e" specialties VOC max. 840 g/l (2007).
<b>Storage</b>	cool and dry; acc. to TRG 300	<b>This product contains:</b>	< 840 g/l VOC

#### Test results

Cross cut test DIN 53151 / ISO 2409	GT 0-1
Salt spray test ISO 9227	100 hours
Humidity test DIN 50017	144 hours GT 0
T-bend test 5 mm	<input checked="" type="checkbox"/>
UV-durable	---
Minimum film thickness	approx. 40 µm

#### Product features

Weather resistant  
 Impact resistant  
 Car wash-resistant  
 Good adhesion  
 Quick drying  
 Short-term resistance to oil and petrol

#### Applications

Decorative and protective paint for e.g. metal and plastic rims, steel pipe structures, air conditioning and ventilation systems, automotilbe/trailer parts, bicycles and motorcycles.

For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.  
 The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.  
 We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Güntersthal 4 / 91235 Hartentstein / Germany  
 Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com