

## Technical Data

# Alu Spray high gloss Chrome wipe resistant

For indoor and outdoor applications

Technical details SPRAY		Advice for handling	
<b>Colour shade</b>	chrome silver	<b>Application temperature</b>	ideal at approx. +18 - 25 °C
<b>Degree of gloss</b>	metallic gloss	<b>Surface preparation</b>	clean, dry, free of grease and rust
<b>Base of binder</b>	natural binder	<b>Primer</b>	if necessary, ECKART Wheel rim black mat
<b>Base of pigment</b>	special aluminium	<b>Touch dry at +20 °C</b>	after approx. 15 - 20 min.
<b>Temperature stability</b>	up to approx. +200 °C	<b>Fully hardened</b>	after approx. 4-6 hours
<b>Flash point/aerosol paint</b>	below +21 °C	<b>Recoat</b>	after approx. 4 hours
<b>Danger class</b>	acc. to TRG 300		
<b>Marking</b>	Danger! Please see MSDS		
<b>Propellant agent</b>	propane/butane	<b>Categorisation according to VOC directive: 2004/42 EG</b>	Category "B/e" specialties VOC max. 840 g/l (2007).
<b>Storage</b>	cool and dry; acc. to TRG 300	<b>This product contains:</b>	< 840 g/l VOC

### Test results

Cross cut test DIN 53151 / ISO 2409	GT 0
Salt spray test ISO 9227	---
Humidity test DIN 50017	144 h GT 0
T-bend test 5 mm	<input checked="" type="checkbox"/>
UV-durable	---
Minimum film thickness	approx. 10 µm

### Product features

Very brilliant, mirror-like gloss  
High opacity  
Quick drying  
Good adhesion  
wipe resistant

### Applications

Especially for artistic and decorative design elements e.g. for trade shows, samples, visual enhancement, creative handicrafts.

Suitable for metal and most of the common plastics.

For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany  
Tel.: +49-(0)9152-77 0 / Fax: +49-(0)9152-77 4435 / E-mail: info.eckart@altana.com