

Technical Data

Aluminum Spray leafing

For indoor and outdoor applications

Technical details SPRAY		Advice for handling	
Colour shade	silver	Application temperature	ideal at approx. +18 - 25 °C
Degree of gloss	metallic glossy	Surface preparation	clean, dry, free of grease and rust
Base of binder	synthetic resin combination	Primer	if necessary ECKART zinc dust primer*
Base of pigment	aluminum	Touch dry at +20 °C	after approx. 10 min.
Temperature stability	up to + 500 °C	Fully hardened	after approx. 4-6 hours
Flash point/aerosol paint	below +21 °C	Recoat	after approx. 6 hours
Danger class	acc. to TRG 300		* up to 400 °C
Marking	Danger! Please see MSDS		
Propellant agent	Dimethylether	Categorisation according to VOC directive: 2004/42 EG	Category "B/e" specialties VOC max. 840 g/l (2007).
Storage	cool and dry; acc. to TRG 300	This product contains:	< 840 g/l VOC

Test results

Cross cut test DIN 53151 / ISO 2409	GT 0-1
Salt spray test ISO 9227	---
Humidity test DIN 50017	144 hours GT 0
T-bend test 5 mm	i.O.
UV-durable	---
Minimum film thickness	approx. 10 µm

Product features

Good adhesion
Wipe resistant
Rust resistant in combination with primer

Applications

For coatings, metal constructions, pipes etc.
Suitable for metal, most of the common plastics and wood.

For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.

The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.
We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Güntersthal 4 / 91235 Hartenstein / Germany

Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com