

## Technical Data

### Stainless Steel bright

For indoor and outdoor applications

Technical details SPRAY		Advice for handling	
Colour shade	steel grey	Application temperature	approx. 18 - 25 °C
Degree of gloss	metallic mat	Surface preparation	clean, dry, free of grease and rust
Base of binder	alkyd resin	Primer	if necessary, ECKART Zinc Spray
Base of pigment	stainless steel	Touch dry at +20 °C	after approx. 10 min.
Temperature stability	up to approx. +240 °C	Fully hardened	after approx. 10 hours
Flash point/aerosol paint	below +21 °C	Recoat	after approx. 8 hours
Danger class	acc. to TRG 300		
Marking	Danger! Please see MSDS		
Propellant agent	Dimethylether	Category "B/e" specialties	VOC max. 840 g/l (2007).
Storage	cool and dry; acc. to TRG 300	VOC directive: 2004/42 EG	< 840 g/l VOC

#### Test results

Cross cut test DIN 53151 / ISO 2409	GT 0-1
Salt spray test ISO 9227	100 hours
Humidity test DIN 50017	--
T-bend test 5 mm	<input checked="" type="checkbox"/>
UV-durable	<input checked="" type="checkbox"/>
Minimum Film thickness	approx. 40 µm

#### Product features

Good corrosion protection due to stainless steel pigment  
 Weather resistant  
 Very good adhesion  
 Flexible Lacquer  
 Quick drying  
 Short-term resistance to oil and petrol

#### Applications

Suitable for technical applications e.g. pipes, steel pipe structures, automobile/trailer parts, bicycles and motorcycles, automobile rims, wrought iron.  
 For repairing stainless steel and embellishing and accentuating decorative objects and DIY.  
 Suitable for metal, wood, cardboard and most of the common plastics.

For absorbent grounds an appropriate sealing coat (e.g. dispersion paint) is recommended.

Store in a dry place and at room temperature (15-25°C), minimum durability two years.

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.  
 The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.  
 We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany  
 Tel.: ++ 49-(0)9152-77 0 / Fax: ++49-(0)9152-77 4435 / E-mail: info.eckart@altana.com