

GELWHITE-H XR

Gelling Agent for Water Phases in Cosmetic Applications

Product Data

INCI Name

Bentonite

Product Description

GELWHITE-H XR is a highly purified white bentonite manufactured from carefully selected, extremely pure ore deposits. GELWHITE-H XR is used as a thixotropic agent in water-based systems for excellent anti-settling and stabilizing properties. GELWHITE-H XR has been sterilized by gamma irradiation.

Typical Properties

The values indicated in this data sheet are typical and do not constitute specification limits.

Form:	Fine powder
Color:	White
Water Content:	5.0 % - 8.0 %
Wet Sieve +200 mesh:	0.0 %
pH Value (2 % suspension in water):	9.5 - 10.5
G.E. Brightness:	min. 77
Swelling (2g in 100 mls):	min. 24.0
Gel Formation:	max. 2.0 ml
Arsenic:	< 5 ppm
Lead:	< 40 ppm
XRD Powder:	Pass
X-Ray Diffraction (PE Glycol):	Pass
E.coli (Neg.):	Pass
Anaerobic Plate Count (max. 100cfu/g):	Pass
Bentonite USP-Test	Pass

Recommended Use

Application areas:	Personal Care:	Cream and Lotion Anti-wrinkle Lotion (e.g. with fruit acids) Sunscreen Product Antiperspirant Facial mask Bath and Shower Gel
	Color Cosmetics:	Liquid Make-up Foundation Blush Eye Product

Incorporation and Processing Instructions

To get the optimum efficiency, a complete dispersion of the material is required. Therefore GELWHITE-H XR should be incorporated applying high shear forces e.g. by using a dissolver or a mill. To facilitate the dispersion, warm water can be used. GELWHITE-H XR is then added slowly to the water (emulsion) under slow agitation. GELWHITE-H XR can also be incorporated as powder added to the grind base.

GELWHITE-H XR

Data Sheet
Issue 11/2018

GELWHITE-H XR can also be used as pre-manufactured pre-gel (containing 5 – 10 % GELWHITE-H XR). To avoid post thickening effects, this pre-gel should be allowed to age overnight. Stirring for approx. 15 minutes under high shear is therefore recommended.

Recommended Levels

GELWHITE-H XR can be used to thicken and stabilize emulsions. Depending on requirements, between 1% and 10 % of GELWHITE-H XR (based upon total formulation weight) is used.

These levels are suggested as guideline; optimum levels can be determined by laboratory tests.

Special Note

GELWHITE-H XR exhibits low acid demand and interacts with both inorganic and organic cations. In formulations that requires tightly controlled rheology and reduced syneresis or that are acidic in pH, GELWHITE-H XR is ideally suited. GELWHITE-H XR is purely inorganic and stable against diluted acids and bases. Gels produced with GELWHITE-H XR withstand oxidation or microbial degradation. GELWHITE-H XR is compatible with anionic and nonionic surfactants.

Storage and Transportation

GELWHITE-H XR should be stored dry in unopened, original packaging at temperature between 0°C and 30°C.

BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ACTAL®, ADJUST-4®, ADVITROL®, BENTOLITE®, CLAYTONE®, CLOISITE®, COPISIL®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SCP®, TIXOGEL®, Y25® are registered trademarks of BYK Additives.

ANTI-TERRA®, BYK®, BYK-DYNWET®, BYK-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany